



0.025mm to 21mm (.001" to .827")



Order 3m to 3t (10 ft to 6000 Lbs)



Delivery: within 3 weeks





**Packaging** 

Coils

Spools

Bars or lengths



## Technical Datasheet Rev.1





Key Features	Typical Applications
Exceptional strength at elevated temperatures and is the highest performing hot cutting wire we offer.	Production lines cutting foam polystyrene (EPS), thermal laminate materials etc. Excellent track record for working continuously and on oscillating cutting frames

Density	8.25 g/cm <sup>3</sup>	0.298 lb/in <sup>3</sup>
Electrical Resistivity at 20 °C	131 microhm • cm	788 ohm • Circ • mil/ft
Maximum Operating Temperature	300 °C	572 °F
Melting Point	1345 ℃	2450 °F
Coefficient of Expansion	13.6 μm/m °C (20 – 100 °C)	7.41 x 10 <sup>-6</sup> in/in °F (70 – 212 °F)





